



GUBI

GUBI Leather Collection

Basic



Brandy



Black

Basic

Type Corrected leather

Thickness 0.9-1.1 mm

Size Average 3.75 m²

Origin India

Tannage Chrome

Dry flexing resistance / number of motions ≥ 20.000 cycles

Fastness to light ≥ 5

Rubbing resistance, dry, 500 cycles ≥ 4

Rubbing resistance, wet, 250 cycles ≥ 3/4

Tear strength ≥ 20

Fire tests -

Tangier

Type Corrected leather

Thickness 1.0-1.2 mm

Size 4.8-5.0 m²

Origin Italy

Tannage Chrome

Dry flexing resistance / number of motions ≥ 30.000 cycles

Fastness to light ≥ 3

Rubbing resistance, dry, 100 cycles ≥ 4

Rubbing resistance, wet, 20 cycles ≥ 4

Tear strength ≥ 20

Fire tests Cigarette test (California)

Chamois

Type Aniline dyed, nubuck finishing

Thickness 1.2 - 1.4 mm

Size Average 5.0 m²

Origin Italy

Tannage Chrome

Dry flexing resistance / number of motions ≥ 50.000 cycles

Fastness to light ≥ 2

Rubbing resistance, dry, 50 cycles ≥ 3

Rubbing resistance, wet, 10 cycles ≥ 3

Tear strength ≥ 20

Fire tests -

Care & Cleaning

Avoid bar soap, saddle soap, leather cleaners, household detergents or chemical products.
Protect from direct sunlight, excessive heat and sharp objects.